RESISTOR FOR CATHODE-RAY TUBE, METHOD FOR PRODUCING THE
SAME, CATHODE-RAY TUBE, AND FED INCLUDING THE RESISTOR

BACKGROUND OF THE INVENTION

1. FIELD OF THE INVENTION:

The present invention relates to a resistor having a high area resistance value usable in an image and video display device utilizing an electron source, for example, a cathode-ray tube (hereinafter, referred to as a "CRT") or a field emission display (hereinafter, referred to as an "FED"), a method for producing such a resistor, a cathode-ray tube including such a resistor, and an FED including such a resistor.

2. DESCRIPTION OF THE RELATED ART:

Figure 6 is a schematic cross-sectional view of a conventional CRT 600 used in a color display apparatus. As shown in Figure 6, the CRT 600 includes a face plate 601 acting as a fluorescent screen and a neck 602. The neck 602 accommodates a cathode 603 and an electronic lens system 607. The electronic lens system 607 includes a triode section 604 and a main electronic lens section 605 formed of a plurality of metal cylinders 605A and 605B. The electronic lens system 607 is structured so as to project a crossover image of an electronic beam from the cathode section 603 on the face plate 601 using the main electronic lens section 605. Reference numeral 606 represents a built-in division-type resistor.

In the electronic lens system 607 having such a structure, a diameter DS of a spot image on the face plate 601 is found by expression (1) using an electrooptic magnitude M and a spherical aberration coefficient CS0.

$$DS=[(M{\times}dx+(1/2)M{\times}CS0{\times}\alpha0^{3})^{2}+DSC^{2}]^{1/2} \quad \ldots \quad (1),$$

where dx is a virtual crossover diameter, $\alpha 0$ is a divergence angle of the beam, and DSC is a divergence component of the beam caused by the repulsive effect of a spatial charge.

Recently, efforts have been made to minimize the spherical aberration coefficient CS0 of the main electronic lens section **605** in order to provide a high precision image by minimizing the spot diameter DS on the face plate **601**.

Japanese Laid-Open Publication No. 61-147442, for example, discloses a method for reducing the spherical aberration coefficient CS0 by a built-in division-type resistor. Japanese Laid-Open Publication Nos. 60-208027 and 2-276138, for example, each disclose a method for reducing the spherical aberration coefficient CS0 by forming a convergence electrode of a spiral resistor in the neck of the CRT instead of forming a convergence electrode of the main electronic lens including a plurality of metal cylinders.

The division-type resistor and the spiral resistor are formed in the following manner as described in, for example, Japanese Laid-Open Publication Nos. 61-224402 and 6-275211.

A film is formed of a stable suspension including ruthenium hydroxide ($Ru(OH)_3$) and glass particles and excluding an organic binder. The film is formed on an inner surface of a glass tube (formed of, for example, low melting point lead glass having a softening point of 640°C) by dipping. The film is dried, and then cut into a spiral pattern. Then, the film is baked at a temperature of 400°C to 600°C to form

a resistor including ruthenium oxide (RuO_2).

Japanese Laid-Open Publication Nos. 61-147442, 55-14627 and 6-275211 disclose another resistor having a high area resistance value, which is formed of RuO_2 and high melting point glass particles.

The resistor formed of RuO_2 and glass particles is formed in a zigzag pattern on an alumina (e.g., Al_2O_3) substrate by screen printing. Such a resistor (referred to as a "glaze resistor") has a total resistance value of 300 MΩ to 1000 MΩ. The alumina used as the substrate has a thermal expansion coefficient of $75 \times 10^{-7}/°C$ and a melting point of 2,050°C. Since a CRT requires a resistor which is highly reliable against a high voltage of about 30 kV and an electronic beam, the resistor formed of RuO_2 and glass particles is formed by baking at a relatively high temperature of 750°C to 850°C.

Japanese Laid-Open Publication No. 7-309282, for example, discloses still another resistor formed of RuO_2 and low melting point glass. The low melting point glass is, for example, $PbO-B_2O_3-SiO_2$-based glass and includes PbO at 65% or more by weight. The softening point of the low melting point glass is about 600°C or less.

The above-described spiral or zigzag-pattern resistors are provided in the neck of the CRT in order to minimize the spot diameter on the fluorescent screen and the deflecting power. In addition, a double anode CRT is also developed in which the electronic lens system includes a high resistance layer in a funnel portion thereof.

A resistor used in the electronic lens system of the CRT provides a potential distribution between the anode electrode and a focus electrode, and thus needs to have a sufficiently high area resistance value of 1 GΩ/$\square$ to 100 GΩ/$\square$ (i.e., about 10^9 Ω/$\square$ to about 10^{11} Ω/$\square$) in order to prevent a current flow sufficiently to avoid sparking and arc discharge.

Displays utilizing an electron source, such as an FED, also require a high area resistance value provided between an anode and a cathode.

According to the method described in Japanese Laid-Open Publication Nos. 61-224402 and 6-275211, Ru(OH)$_3$, which is an insulating substance, is thermally decomposed while being baked at a temperature of 400°C to 600°C. By such thermal decomposition, RuO$_2$, which is a conductive substance, is deposited, and the low melting point glass flows. As a result, fine particles of RuO$_2$ having a diameter of 0.01 to 0.03 μm are deposited around the glass particles, which form a resistor.

Such a method has the following problems in obtaining a high resistance value of 5 GΩ to 20 GΩ (area resistance value: 1 MΩ/$\square$ to 4 MΩ/$\square$): (i) the dependency of the area resistance value on the baking temperature increases (i.e., the area resistance value significantly changes when the baking temperature slightly changes); (ii) the temperature coefficient of resistance value (TCR) is increased in a negative direction; and (iii) the load characteristic over a long period of time is inferior. The expression "/$\square$" refers to "per unit area".

The method described in Japanese Laid-Open Publication Nos. 55-14527, 61-147442 and 6-275211 has a problem in that the resultant resistor cannot be formed on an inner surface of the low melting point glass (having a softening point of 640°C) used for the CRT due to the high baking temperature of 750°C to 850°C.

According to the method described in Japanese Laid-Open Publication No. 7-309282, the resistor can be formed on an inner surface of the CRT at a low temperature of 440°C to 520°C. However, the resistor formed by this method has problems in that (i) the area resistance value significantly changes in accordance with the load characteristic (against application of a voltage of 30 kV at 70°C at 10^{-7} Torr) in the vacuum over a long period of time (5,000 hours); and (ii) the spot diameter on the fluorescent screen is increased due to the load since the TCR is negative.

A tungsten (W)-aluminium oxide-based cermet resistor having a high area resistance value has been developed for use in the electronic tube (see, for example, Japanese Publication for Opposition No. 56-15712). Such a resistor has problems in that (i) a high area resistance value of 10^9 $\Omega/\square$ or more is not obtained; and (ii) the TCR is negative and the absolute value thereof is excessively large.

A resistor having an area resistance value of 1 GΩ/$\square$ to 100 GΩ/$\square$ does not need to be shaped into a spiral or zigzag pattern, for use in a CRT. However, the conventional resistive materials have an area resistance value of 1 MΩ/$\square$ to 100 MΩ/$\square$. Since such a range of area resistance

values is not sufficiently high, the resistor needs to be shaped into a spiral or zigzag pattern.

Attempts have been made to produce an electronic lens system using a high resistance ceramic cylinder without shaping the resistor into a spiral or zigzag pattern (see, for example, Japanese Laid-Open Publication No. 6-275211 and the Proceedings of the 14th International Display Research Conference, pp. 229 to 232 (1994)).

The resistive materials used for this type of electronic lens system include forsterite ($2MgO \cdot SiO_2$)-based and $Al_2O_3-MnO_2-Fe_2O_3-Nb_2O_3$-based materials. The specific resistance value of these materials is 10^{11} Ωcm (resistance value: 2.4 GΩ to 240 GΩ). However, it has been pointed out that when the power consumption of a display apparatus, for example, a TV is increased by the negative TCR, the current flowing in the resistive material rapidly increases and possibly thermal runaway occurs.

SUMMARY OF THE INVENTION

According to one aspect of the invention, a resistor includes a mixture of at least one of a metal conductive oxide and a transition metal material with an insulating oxide.

In one embodiment of the invention, the resistor is produced using a flame-spraying method.

In one embodiment of the invention, the flame-spraying method includes plasma flame-spraying.

In one embodiment of the invention, the flame-spraying method includes laser flame-spraying.

In one embodiment of the invention, the metal conductive oxide is at least one material selected from the group consisting of titanium oxide, rhenium oxide, iridium oxide, ruthenium oxide, vanadium oxide, rhodium oxide, osmium oxide, lanthanum titanate, $SrRuO_3$, molybdenum oxide, tungsten oxide, and niobium oxide.

In one embodiment of the invention, the metal conductive oxide is at least one material selected from the group consisting of TiO, ReO_3, IrO_2, RuO_2, VO, RhO_2, OsO_2, $LaTiO_3$, $SrRuO_3$, MoO_2, WO_2, and NbO.

In one embodiment of the invention, the transition metal material is at least one material selected from the group consisting of titanium, rhenium, vanadium, and niobium.

In one embodiment of the invention, the insulating oxide is at least one material selected from the group consisting of alumina, silicon oxide, zirconium oxide, and magnesium oxide.

In one embodiment of the invention, the insulating oxide is at least one material selected from the group consisting of Al_2O_3, SiO_2, ZrO_2, and MgO.

In one embodiment of the invention, the metal conductive oxide is TiO, and the insulating oxide is Al_2O_3.

In one embodiment of the invention, the resistor has

an area resistance value of at least of about 1 GΩ/□.

According to another aspect of the invention, a cathode ray tube includes the above-described resistor.

According to still another aspect of the invention, a method for producing a resistor includes the steps of forming an electrode on one of an alumina substrate, a glass substrate and a glass tube; and flame-spraying a mixture of at least one of a metal conductive oxide and a transition metal material with an insulating oxide, thereby depositing the mixture on the one of the alumina substrate, the glass substrate and the glass tube.

According to still another aspect of the invention, a field emission display includes an anode; a cathode; and a resistor provided between the anode and the cathode. The resistor includes a mixture of at least one of a metal conductive oxide and a transition metal material with an insulating oxide. The resistor is formed using a flame-spraying method. The resistor has an area resistance value of at least about 1 GΩ/□.

In one embodiment of the invention, the field emission display further includes a support provided between the anode and the cathode, wherein the support is covered with the resistor.

In one embodiment of the invention, the support includes at least one of glass and alumina.

In one embodiment of the invention, the metal conductive oxide is at least one material selected from the

group consisting of titanium oxide, rhenium oxide, iridium oxide, ruthenium oxide, vanadium oxide, rhodium oxide, osmium oxide, lanthanum titanate, $SrRuO_3$, molybdenum oxide, tungsten oxide, and niobium oxide.

In one embodiment of the invention, the metal conductive oxide is at least one material selected from the group consisting of TiO, ReO_3, IrO_2, RuO_2, VO, RhO_2, OsO_2, $LaTiO_3$, $SrRuO_3$, MoO_2, WO_2, and NbO.

In one embodiment of the invention, the transition metal material is at least one material selected from the group consisting of titanium, rhenium, vanadium, and niobium.

In one embodiment of the invention, the insulating oxide is at least one material selected from the group consisting of alumina, silicon oxide, zirconium oxide, and magnesium oxide.

In one embodiment of the invention, the insulating oxide is at least one material selected from the group consisting of Al_2O_3, SiO_2, ZrO_2, and MgO.

In one embodiment of the invention, the metal conductive oxide is TiO, and the insulating oxide is Al_2O_3.

According to the present invention, a resistor having a satisfactorily high area resistance value, a satisfactory load characteristic in vacuum, and a positive and stable TCR is obtained without a baking process.

Such a resistor is obtained by flame-spraying a

mixture of both or either of a metal conductive oxide or a transition metal material and an insulating oxide toward a substrate using plasma torch or laser. Usable metal conductive oxides include, for example, TiO, ReO_3, IrO_2, MoO_2,

5   WO_2, RuO_2, and $LaTiO_2$. Usable transition metal materials include, for example, Ti, Re, V and Nb. Usable insulating oxides include, for example, SiO_2, Al_2O_3, ZrO_2, and MgO.

Since the particles of the metal conductive oxide

10   or the transition metal material are dispersed among the particles of the insulating oxide, the resistor formed of the above-described mixture has a sufficiently high area resistance value.

The present inventors have found that (i) by using

15   an appropriate metal conductive oxide and/or transition metal material and insulating oxide at an appropriate ratio and an appropriate flame-spraying method, a resistor having a high area resistance value of about 1 GΩ/$\square$ to about

20   100 GΩ/$\square$ is produced; (ii) the resultant resistor has a superior overtime load characteristic to the conventional resistors; and (iii) the TCR of the resultant resistor is small and stable.

25   Such a resistor does not need to be shaped into a spiral or zigzag pattern and can be easily formed on an alumina substrate of an inner surface of the funnel of a CRT.

30   Thus, the invention described herein makes possible the advantages of providing (1) a resistor having a satisfactorily high area resistance value produced without baking; (2) a resistor having a satisfactorily high load

characteristic over a long period of time in vacuum; (3) a reliable resistor having a small TCR; (4) a method for producing such a resistor; (5) a CRT including such a resistor; and (6) an FED including such a resistor.

These and other advantages of the present invention will become apparent to those skilled in the art upon reading and understanding the following detailed description with reference to the accompanying figures.

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1A is a schematic view of a plasma flame-spraying apparatus used for producing a resistor in a first example according to the present invention;

Figure 1B is a flowchart illustrating a method for producing the resistor shown in Figure 1A;

Figure 2 is a schematic cross-sectional view of a CRT including the resistor shown in Figure 1A;

Figure 3A is a schematic view of a laser flame-spraying apparatus used for producing a resistor in a second example according to the present invention;

Figure 3B is a flowchart illustrating a method for producing the resistor shown in Figure 3A;

Figure 4 is a schematic cross-sectional view of a CRT including the resistor shown in Figure 3A;

Figure 5A is an isometric view of an FED in a third

example according to the present invention;

Figure 5B is a cross-sectional view of the FED shown in Figure **5A** taken along surface **A**; and

Figure 6 is a schematic cross-sectional view of a conventional CRT.

DESCRIPTION OF THE EMBODIMENTS

Hereinafter, the present invention will be described by way of illustrative examples with reference to the accompanying drawings.

(Example 1)

A resistor produced by a plasma flame-spraying method in a first example according to the present invention will be described with reference to Figures **1A**, **1B** and **2**.

Figure **1A** is a schematic view of a plasma flame-spraying apparatus **100** used for producing a resistor in the first example. Figure **1B** is a flowchart illustrating a method for producing the resistor in the first example.

As shown in Figure **1A**, the plasma flame-spraying apparatus **100** includes a negative electrode **101**, a positive electrode **102**, a power supply **103**, a spray nozzle **107**, and a powder supply port **109** for supplying a resistive material **108**. Reference numeral **104** represents a DC arc, and reference numeral **105** represents operation gas. Reference numeral **106** represents an arc plasma jet **106**. Reference numeral **110** represents an alumina (e.g., Al_2O_3) substrate, and reference numeral **111** represents an electrode (for

example, focus electrode and anode electrode). Reference numeral **112** represents a resistor produced by the plasma flame-spraying apparatus **100**. A glass substrate may be used instead of the alumina substrate **110**.

With reference to Figure 1B, a method for producing the resistor **112** will be described. Refer to Figure 1A for the reference numeral of each element.

In step S101, a silver paste, for example, is screen-printed on the alumina substrate **110** and then baked, thereby forming the electrodes **111**.

Then, in step S102, an electric field is applied between the negative electrode **101** and the positive electrode **102** using the power supply **103** to generate the DC arc **104**. The operation gas **105** (e.g., argon-hydrogen mixture gas or nitrogen-hydrogen mixture gas) is caused to flow along a surface of the negative electrode **101** to generate the arc plasma jet **106**.

In step S103, the resistive material **108** including, for example, a mixture powder including TiO at about 30% by weight and Al_2O_3 at about 70% by weight is supplied from the power supply port **109**. While the spray nozzle **107** is moved toward the alumina substrate **110**, the resistive material **108** is flame-sprayed toward the alumina substrate **110** to a thickness of about 20 μm, thereby forming the resistor **112** on the alumina substrate **110**. In the case where the resistive material **108** needs to be flame-sprayed under a low pressure atmosphere of about 0.1 to about 10 Torr, the plasma flame-spraying apparatus **100** is entirely accommodated in a low pressure chamber before the

production.

Then, Al_2O_3 is sprayed toward the resistor 112 to a thickness of about 40 μm, thereby forming a protective film (not shown). Al_2O_3 is not sprayed to the electrodes 111. Thus, a resistor section 113 including the TiO-Al_2O_3-based resistor 112, the alumina substrate 110 and the electrodes 111 is formed.

The TiO-Al_2O_3-based resistor 112, which is produced without a baking process, has a high area resistance value of about 1 GΩ/□ or more and also a satisfactory heat-resistant load characteristic as described below. Furthermore, the TiO-Al_2O_3-based resistor 112 has a positive and stable TCR.

Figure 2 is a schematic cross-sectional view of a CRT 200 including the resistor section 113. Identical elements previously discussed with respect to Figure 6 bear identical reference numerals and the descriptions thereof will be omitted.

The resistor section 113, as described above with reference to Figure 1A, includes the TiO-Al_2O_3-based resistor 112, the alumina substrate 110 and the electrodes 111.

The CRT 200 including the TiO-Al_2O_3-based resistor 112 enjoys the above-described advantages of the TiO-Al_2O_3-based resistor 112.

The present invention is not limited to the TiO-Al_2O_3-based resistor 112. Usable instead of TiO are both

or either of a metal conductive oxide or a transition metal material. Usable instead of Al_2O_3 is an insulating oxide.

(Example 2)

5   A resistor produced by a laser flame-spraying method in a second example according to the present invention will be described with reference to Figures **3A**, **3B** and **4**.

       Figure **3A** is a schematic view of a laser flame-
10   spraying apparatus **300** used for producing a resistor in the second example. Figure **3B** is a flowchart illustrating a method for producing the resistor in the second example.

       As shown in Figure **3A**, the laser flame-spraying
15   apparatus **300** includes a spray nozzle **201**, a powder supply port **202** for supplying a resistive material (not shown), and a laser light collection lens system **204**. The powder supply port **202** is formed so as to run throughout the spray nozzle **201**. Reference numeral **203** represents laser light.
20   Reference numeral **205** represents a glass tube of a CRT, and reference numeral **206** represents an electrode. Reference numeral **207** represents a resistor produced by the laser flame-spraying apparatus **300**.

25   With reference to Figure **3B**, a method for producing the resistor **207** will be described. Refer to Figure **3A** for the reference numeral of each element.

       In step **S301**, the electrodes **206** (for example, anode
30   electrode and focus electrode) are formed on an inner surface of the glass tube **205** of the CRT. The electrodes **206** can be formed of the same material and in the same manner as those of the electrodes **111** described in the first example.

Then, in step S302, the laser light 203 is collected by the laser light collection lens system 204. In step S303, a resistive material (not shown) including, for example, a mixture powder including TiO at about 10% by weight and Al_2O_3 at about 90% by weight is supplied from the power supply port 202. While the spray nozzle 201 is moved toward the glass tube 205, the resistive material is flame-sprayed toward the glass tube 205 to a thickness of about 20 µm, thereby forming resistor 207 on the glass tube 205. Since the resistor 207 is formed on the inner surface of the glass tube 205, it is not necessary to form a protective film as is necessary in the first example.

The $TiO-Al_2O_3$-based resistor 207, which is produced without a baking process, has a high resistance value of about 1 GΩ and also a satisfactory heat-resistant load characteristic as described below. Furthermore, the $TiO-Al_2O_3$-based resistor 207 has a positive and stable TCR.

Figure 4 is a schematic cross-sectional view of a CRT 400 including the $TiO-Al_2O_3$-based resistor 207.

The CRT 400 includes the $TiO-Al_2O_3$-based resistor 207 provided on the inner surface of the glass tube 205, and the electrodes 206. An inner surface 401 of the CRT 400 is coated with a paste of graphite, RuO_2 or the like.

The CRT 400 including the $TiO-Al_2O_3$-based resistor 207 enjoys the above-described advantages of the $TiO-Al_2O_3$-based resistor 207.

The present invention is not limited to the TiO-

Al_2O_3-based resistor **207**. Usable instead of TiO are both
or either of a metal conductive oxide or a transition metal
material. Usable instead of Al_2O_3 is an insulating oxide.

5   (Example 3)
        In a third example, an FED **500** including a resistor
according the present invention will be described with
reference to Figure **5A** and **5B**.

10   Figure **5A** is an isometric view of the FED **500**.
Figure **5B** is a cross-sectional view of the FED **500** taken
along surface **A** in Figure **5A**.

        As shown in Figures **5A** and **5B**, the FED **500** includes
15 an anode **501**, a cathode **502**, an FED array **503** provided on
an inner surface of the cathode **502**, a cathode drawing
electrode **504** connected to the cathode **502**, an anode drawing
electrode **505** connected to the anode **501**, a fluorescent body
508 provided on an inner surface of the anode **501**, and a
20 power supply **507**.

        Supports **506** are provided between the anode **501** and
the cathode **502** for preventing the anode **501** and the cathode
502 from contacting each other in vacuum. The supports **506**
25 are formed of glass, alumina or any other insulating
material.

        The supports **506** are covered with the TiO-Al_2O_3-
based resistor **112** described in the first example or the
30 TiO-Al_2O_3-based resistor **207** in the second example.

        Without such a resistor, the following
inconvenience occurs. When a high voltage of several

kilovolts to several tens of kilovolts is applied between the anode drawing electrode **504** and the cathode drawing electrode **505**, electrons are accumulated in the supports **506** since the supports **506** are formed of an insulating

5   material. When the electrons are accumulated in the supports **506**, arc or spark is generated from the supports **506**. As a result, an image on a screen of the FED **500** is disturbed or the fluorescent body **508** is damaged.

10   In the FED **500** including the above-described resistor, the electrons accumulated in the supports **506** are removed by causing a slight amount of current to flow in the supports **506**. Accordingly, the electrons are not accumulated, which prevents generation of arc or spark from

15   the supports **506** or damages on the fluorescent body **508**.

[Specific Examples]

TiO and Al_2O_3-based resistors are produced with various ratios of TiO and Al_2O_3. Resistors including both or either of a metal conductive oxide or a transition metal

20   material (e.g., ReO_3, IrO_2, MoO_2, WO_2, RuO_2, $LaTiO_3$, or TiO_{2-x} ($0<x<1$)), and an insulating oxide (e.g., SiO_2, ZrO_2, or MgO) are also produced with various ratios.

25   The resistors are produced by a plasma flame-spraying method or a laser flame-spraying method.

The resultant resistors are each attached to an electronic gun of the CRT **200** (Figure **2**) or the CRT **400** (Figure

30   **4**), or provided on the supports **506** of the FED **500** (Figures **5A** and **5B**).

An accelerated test of the CRT **200** can be performed

by applying a voltage of about 30 kV to about 40 kV to the anode electrode (e.g., electrode **111** in Figure **1A**) and applying a voltage of about 5 kV to about 10 kV to the focus electrode (e.g., electrode **111** in Figure **1A**). In this example, a voltage of about 30 kV is applied to the anode electrode for about 5,000 hours for testing the life of the CRT **200** (test of actual life). A voltage of about 45 kV is applied to the anode electrode for about 10 hours for testing the life of the CRT **200** when an excessive load is applied (test of life against short-time application of excessive load).

An accelerated test of the CRT **400** can be performed by applying a voltage of about 10 kV to about 30 kV between the electrodes **206**. In this example, a voltage of about 30 kV is applied between the electrodes **206** for about 5,000 hours for testing the life of the CRT **400** (test of actual life). A voltage of about 45 kV is applied to the anode between the electrodes **206** for about 10 hours for testing the life of the CRT **400** when an excessive load is applied (test of life against short-time application of excessive load).

An accelerated test of the FED **500** is performed by applying a voltage of about 15 kV between the anode drawing electrode **504** and the cathode drawing electrode **505**. An area resistance value, temperature characteristic of resistance value (TCR), and overtime change in the area resistance value, and the like are evaluated.

The conditions for producing the resistors are shown in Tables 1 through 4. The evaluation results are shown in Tables 5 and 6. Samples 15 through 19 in Table 2 are

conventional resistors.

Table 1

Sample	Materials and ratio (% by weight)		Method for film formation	Substrate	Use	Pattern of resistor
	Metal conductive oxide	Insulating oxide				
1	TiO (30)	Al_2O_3 (70)	Plasma flame-spraying (Ar-H_2 gas)	Alumina (Al_2O_3)	Division-type resistor	Plain
2	TiO (5)	Al_2O_3 (95)	Plasma flame-spraying (N_2-H_2 gas)	Alumina (Al_2O_3)	Division-type resistor	Plain
3	TiO (3)	Al_2O_3 (97)	Laser flame-spraying	Alumina (Al_2O_3)	Division-type resistor	Plain
4	ReO_3 (5)	SiO_2 (95)	Laser flame-spraying	Alumina (Al_2O_3)	Division-type resistor	Plain
5	IrO_2 (5)	ZrO_2 (95)	Plasma flame-spraying (N_2-H_2 gas)	Alumina (Al_2O_3)	Division-type resistor	Plain
6	RuO_2 (3)	MgO (97)	Plasma flame-spraying (Ar-H_2 gas)	Alumina (Al_2O_3)	Division-type resistor	Plain
7	VO (5)	Al_2O_3 (95)	Plasma flame-spraying (Ar-H_2 gas)	Alumina (Al_2O_3)	Division-type resistor	Plain
8	RhO_2 (4)	Al_2O_3 (96)	Laser flame-spraying	CRT glass tube	Inner surface of CRT	Plain
9	$LaTiO_3$ (5)	Al_2O_3 (95)	Plasma flame-spraying (N_2-H_2 gas)	CRT glass tube	Inner surface of CRT	Plain
10	$SrRuO_3$ (5)	Al_2O_3 (95)	Plasma flame-spraying (N_2-H_2 gas)	CRT glass tube	Inner surface of CRT	Plain

Table 2

Sample	Materials and ratio (% by weight)		Method for film formation	Substrate	Use	Pattern of resistor
	Metal conductive oxide (Except for samples 17, 18 and 19)	Insulating oxide				
11	MoO_2 (5)	Al_2O_3 (95)	Plasma flame-spraying (N_2–H_2 gas)	Alumina (Al_2O_3)	Division-type resistor	Plain
12	WO_2 (5)	Al_2O_3 (95)	Plasma flame-spraying (N_2–H_2 gas)	Alumina (Al_2O_3)	Division-type resistor	Plain
13	NbO (5)	SiO_2 (95)	Plasma flame-spraying (N_2–H_2 gas)	Alumina (Al_2O_3)	Division-type resistor	Plain
14	OsO_2 (5)	SiO_2 (95)	Plasma flame-spraying (N_2–H_2 gas)	Alumina (Al_2O_3)	Division-type resistor	Plain
15*	RuO_2 (3)	Lead-based glass (97) (PbO–SiO_2–B_2O_3–Al_2O_3)	Paste is screen-printed and baked at 800 °C	Alumina (Al_2O_3)	Division-type resistor	Zigzag
16*	RuO_2 (3)	Lead-based glass (97) (PbO–SiO_2–B_2O_3–Al_2O_3)	Paste is screen-printed and baked at 450 °C	CRT glass tube	Inner surface of CRT	Zigzag
17*	Al_2O_3 – MnO_2 – Fe_2O_3 – Nb_2O_3 –based ceramic		Baked		Cylinder in CRT	Zigzag
18*	W (20)	Al_2O_3 (80)	Sputtered and baked at 850 °C in vacuum	Alumina (Al_2O_3)	Division-type resistor	Plain
19*	Mo (20)	Al_2O_3 (80)	Sputtered and baked at 850 °C in vacuum	Alumina (Al_2O_3)	Division-type resistor	Plain

* Samples 15 through 19: conventional resistors

P21168

Table 3

Sample	Materials and ratio (% by weight)		Method for film formation	Substrate	Use	Pattern of resistor
	Metal conductive oxide or transition metal material	Insulating oxide				
20	TiO (10)	Al_2O_3 (90)	Plasma flame-spraying ($Ar-H_2$ gas)	Glass support in FED	Charge prevention (Arc and spark prevention)	Plain
21	$TiO_{1.5}$ (5)	Al_2O_3 (95)	Plasma flame-spraying (N_2-H_2 gas)	Glass support in FED	Charge prevention (Arc and spark prevention)	Plain
22	$TiO_{1.2}$ (3)	Al_2O_3 (97)	Laser flame-spraying	Glass support in FED	Charge prevention (Arc and spark prevention)	Plain
23	ReO_3 (5)	SiO_2 (95)	Laser flame-spraying	Glass support in FED	Charge prevention (Arc and spark prevention)	Plain
24	IrO_2 (5)	ZrO_2 (95)	Plasma flame-spraying (N_2-H_2 gas)	Glass support in FED	Charge prevention (Arc and spark prevention)	Plain
25	RuO_2 (5)	MgO (95)	Plasma flame-spraying ($Ar-H_2$ gas)	Glass support in FED	Charge prevention (Arc and spark prevention)	Plain
26	VO (10)	Al_2O_3 (90)	Plasma flame-spraying ($Ar-H_2$ gas)	Glass support in FED	Charge prevention (Arc and spark prevention)	Plain

Table 4

Sample	Materials and ratio (% by weight)		Method for film formation	Substrate	Use	Pattern of resistor
	Metal conductive oxide or transition metal material	Insulating oxide				
27	RhO_2 (5)	Al_2O_3 (95)	Laser flame-spraying	CRT glass tube	Inner surface of CRT	Plain
28	Ti (5)	Al_2O_3 (95)	Plasma flame-spraying (N_2–H_2 gas)	CRT glass tube	Inner surface of CRT	Plain
29	Re (5)	Al_2O_3 (95)	Plasma flame-spraying (N_2–H_2 gas)	CRT glass tube	Inner surface of CRT	Plain
30	V (5)	Al_2O_3 (95)	Plasma flame-spraying (N_2–H_2 gas)	Glass support in FED	Charge prevention (Arc and spark prevention)	Plain
31	Nb (5)	Al_2O_3 (95)	Plasma flame-spraying (N_2–H_2 gas)	Glass support in FED	Charge prevention (Arc and spark prevention)	Plain

Table 5

Sample	Thickness	Area resistance value	Temperature characteristic of resistance value (TCR) (PPm/°C)	10^{-7} Torr 70°C 30kV: change in area resistance value after 5000 hrs.	45kV: change in area resistance value after 10 hrs.
1	20 μm	1 GΩ	−150	0.3 %	−0.5 %
2	20 μm	10 GΩ	−350	0.25 %	−0.5 %
3	35 μm	100 GΩ	−300	0.2 %	−0.6 %
4	40 μm	15 GΩ	+1500	0.5 %	−0.7 %
5	30 μm	50 GΩ	+1500	0.3 %	−0.8 %
6	30 μm	1 GΩ	+35	0.3 %	−0.7 %
7	30 μm	5 GΩ	−45	0.5 %	−1.2 %
8	30 μm	3 GΩ	+200	0.4 %	−1.0 %
9	30 μm	10 GΩ	−30	0.5 %	−1.5 %
10	30 μm	4 GΩ	−55	0.3 %	−1.3 %
11	30 μm	1 GΩ	−20	−0.8 %	−1.2 %
12	30 μm	2 GΩ	−35	−0.7 %	−1.5 %
13	30 μm	10 GΩ	−18	−0.5 %	−1.0 %
14	30 μm	3 GΩ	+1500	+0.8 %	−0.8 %
15	5 μm	1 GΩ	+340	−1.2 %	−15 %
16	5 μm	10 GΩ	+420	−1.5 %	−20 %

Table 6

Sample	Thickness	Area resistance value	Temperature characteristic of resistance value (TCR) (PPm/°C)	10^{-7} Torr 70°C 30kV: change in area resistance value after 5000 hrs.	45kV: change in area resistance value after 10 hrs.
17	5 μm	100 GΩ	+1500	5.2 %	−15 %
18	5 μm	16 Ω	+11000	−15 %	Cracks in substrate
19	5 μm	26 Ω	+10000	−19 %	Cracks in substrate
20	20 μm	8 GΩ	+50	0.3 %	−0.6 %
21	20 μm	10 GΩ	−103	−0.35 %	−0.5 %
22	20 μm	100 GΩ	−305	−0.3 %	−0.6 %
23	20 μm	5 GΩ	+105	−0.5 %	−0.8 %
24	20 μm	10 GΩ	+10	−0.2 %	−0.7 %
25	20 μm	15 GΩ	+10	0.3 %	−1.0 %
26	20 μm	150 GΩ	−1500	−0.8 %	−1.2 %
27	20 μm	18 GΩ	−150	−0.3 %	−1.0 %
28	20 μm	52 GΩ	−450	−0.5 %	−1.5 %
29	20 μm	30 GΩ	−520	−0.7 %	−1.3 %
30	20 μm	180 GΩ	−1550	−0.8 %	−1.2 %
31	20 μm	205 GΩ	−1630	−0.9 %	−1.2 %

It is appreciated from Tables 1 through 6 that compared to a conventional RuO_2-glass-based resistor, a conventional ceramic resistor, or a conventional cermet resistor including Mo (molybdenum) or W (tungsten) and an insulating oxide, the resistors including both or either of a metal conductive oxide or a transition metal material, and an insulating oxide have a higher area resistance value, exhibit a smaller change in the TCR, and change less in the area resistance value against a load at an area identical resistance value (i.e., have a higher durability against application of a high voltage).

When a high load of about 45 kV is applied, the conventional resistors are significantly damaged since the TCR is negative.

As described above, a resistor according to the present invention is formed of a mixture of both or either of a metal conductive oxide or a transition metal material, and an insulating oxide; and is formed on alumina or glass by a plasma flame-spraying method or a laser flame-spraying method. Such a resistor has a sufficiently high area resistance value and is obtained without a baking process.

Since the particles of the metal conductive oxide or the transition metal material are dispersed among the particles of the insulating oxide, the resistor formed of the above-described mixture has a sufficiently high area resistance value.

The resistor according to the present invention is stable due to a superior load characteristic in vacuum and a small TCR.

The metal conductive oxides usable in the resistor include, for example, titanium oxide, rhenium oxide, iridium oxide, ruthenium oxide, vanadium oxide, rhodium oxide, osmium oxide, lanthanum titanate, $SrRuO_3$, molybdenum oxide, tungsten oxide, and niobium oxide. These oxides can be used independently or in combination of two or more.

Preferably, TiO, ReO_3, IrO_2, RuO_2, VO, RhO_2, OsO_2, $LaTiO_3$, $SrRuO_3$, MoO_2, WO_2, and NbO are used.

The transition metal materials usable in the resistor include, for example, titanium, rhenium, vanadium niobium. These materials can be used independently or in combination of two or more.

The insulating oxides usable in the resistor include, for example, alumina, silicon oxide, zirconium oxide, and magnesium oxide. These materials can be used independently or in combination of two or more.

Preferably, Al_2O_3, SiO_2, ZrO_2, and MgO are used.

Various other modifications will be apparent to and can be readily made by those skilled in the art without departing from the scope and spirit of this invention. Accordingly, it is not intended that the scope of the claims appended hereto be limited to the description as set forth herein, but rather that the claims be broadly construed.